

Ficha Técnica

Artigo:	EF9300				
Composição:	100% Viscose				
Material na Teia:	100% Viscose				
Material na Trama:	100% Viscose				
Fio na Teia:	84 Dtex				
Fio na Trama:	110 Dtex				
Densidade Teia:	46 +/- 2 fios/cm				
Densidade Trama:	27 +/- 1 pas/cm				
Ponto:	Sarja				
Largura:	140 CM (+/- 2 cm)				
Gramagem:	70 Gr/M2 (+/- 5%)				
Acabamento:	Anti-mancha				
Resistência à Tração (ISO 13934-2)	<table> <tr> <td>Teia</td><td>35 +/- 5 Kg</td></tr> <tr> <td>Trama</td><td>30 +/- 5 Kg</td></tr> </table>	Teia	35 +/- 5 Kg	Trama	30 +/- 5 Kg
Teia	35 +/- 5 Kg				
Trama	30 +/- 5 Kg				
Deslizamento Costuras (BS 3320)	<table> <tr> <td>Teia</td><td><7 mm a 6 kg</td></tr> <tr> <td>Trama</td><td><7 mm a 6 kg</td></tr> </table>	Teia	<7 mm a 6 kg	Trama	<7 mm a 6 kg
Teia	<7 mm a 6 kg				
Trama	<7 mm a 6 kg				

DIMENSIONAL STABILITY		
	Warp	Weft
Steaming at 110°C (ISO 3005)	1,5%	1,5%

COLOR FASTNESS		
	Change	Stain
To Rubbing (ISO 105 X12)*	4 - 5	4 - 5
To Dry Washing (ISO 105 D01)	4 - 5	4
To Light (ISO 105 B02)	4 - 5	-
To Perspiration (ISO 105 E04)*	4 - 5	4

Colour fastness may change depending colours.

Test based on different trials, and for all this, are always average values.

* Dark Colors 3-4.

Simbolos de Lavagem:

PUZZLE Perfil, Lda.
Rua da Sobreira, nº 291
4805-438 Ronfe – Guimarães
+351 253 548 218



geral@puzzleperfil.pt
www.puzzleperfil.pt



European Flax.
Premium linen fiber