

Ficha Técnica

Artigo:	EF 9400 Cores
Composição:	100% Poliéster
Material na Teia:	100% Poliéster
Material na Trama:	100% Poliéster
Densidade Teia:	42 +/- 2 fios/cm
Densidade Trama:	30 +/- 1 pas/cm
Fio na Teia:	50 Dtex
Fio na Trama:	78 Dtex
Ponto:	Tafetá
Largura:	158 CM (+/- 2 cm)
Gramagem:	49 Gr/M2 (+/- 5%)
Acabamento:	Anti-estático
Resistência à Tração (ISO 13934-2)	Teia 45 +/- 5 Kg Trama 45 +/- 5 Kg
Deslizamento Costuras (BS 3320)	Teia <6 mm a 6 kg Trama <6 mm a 6 kg

DIMENSIONAL STABILITY		
	Warp	Weft
Steaming at 110°C (ISO 3005)	1,5%	1,5%
Washing at 40°C (ISO 6330)	1,0%	0,5%

COLOR FASTNESS		
	Change	Stain
To Rubbing (ISO 105 X12)*	4 -5	4-5
To Washing at 30°C (ISO 105 C06)	5	4-5
To Dry Washing (ISO 105 D01)	4 -5	4-5
To Light (ISO 105 B02)	4 - 5	-
To Perspiration (ISO 105 E04)*	4 -5	4-5

Colour fastness may change depending colours.

Test based on different trials, and for all this, are always average values.

* Dark Colors 3-4.

PUZZLE Perfil, Lda.
 Rua da Sobreira, nº 291
 4805-438 Ronfe – Guimarães
 +351 253 548 218

geral@puzzleperfil.pt
 www.puzzleperfil.pt



European Flax.
 Premium linen fiber